

PRECIPITATION HARDENING STAINLESS STEEL BAR

TYPICAL APPLICATIONS

Used where high strength and good corrosion resistance are required as well as for applications requiring high fatigue strength, good resistance to galling and stress corrosion resistance. Suitable for intricate parts requiring machining and welding and where freedom for distortion is a requirement. Used in aerospace, defence and offshore oil & gas industries. For missile components, motor shafts, valve stems, gears and other mechanical components.

PRODUCT DESCRIPTION

An American aerospace grade stainless steel that contains 4% copper and may be hardened by a single low-temperature precipitation hardening heat treatment, producing excellent mechanical properties at a high strength level.

Condition: Can be supplied in the annealed condition (Condition A) or heat treated as follows:-

Condition H900 (900°F)	Condition H925 (925°F)
Condition H1025 (1025°F)	Condition H1075 (1075°F)
Condition H1100 (1100°F)	Condition H1150 (1150°F)

to give various property combinations as below. The material should not be used in the annealed condition. This grade of stainless steel has a typical density of 7.75kg/dm³ and can be magnetised.

RELATED SPECIFICATIONS

- AISI 630
- UNS S17400
- ASME SA-564 Type 630

CHEMICAL COMPOSITION (WEIGHT %)

	C	Mn	P	S	Si	Cr	Ni	Cu	Mo	Nb
Min						15.00	3.00	3.00		5 X C
Max	0.07	1.00	0.04	0.03	1.00	17.50	5.00	5.00	0.50	0.45

MECHANICAL PROPERTIES (MINIMA)

Condition	Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on 4D G.L. (%)	Hardness (HB)
H900	1,310	1,172	10	388 / 444
H925	1,172	1,069	10	375 / 429
H1025	1,069	1,000	12	331 / 401
H1075	1,000	862	13	311 / 375
H1100	965	793	14	302 / 363
H1150	931	724	16	277 / 352

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

STOCK RANGE

**Round Bar : 0.080" up to 14" Diameter
(2.03 to 355.6mm)**

Various in Square, Flat & Hexagon.

CUT TO SIZE SAWN BLANKS

Cut to length in house to tolerances - Nil + 1.0mm

MACHINABILITY

In annealed condition surface cutting speed of 80 ft/min and a machinability rating of 50% of B-112 rated at 100%. Over-aged condition, 130 ft/min and 75% of B-1112 rated at 100%.

CORROSION RESISTANCE

Superior to straight chromium grades like 410, approaching corrosion resistance of the chromium nickel grades. In many corrosive media it is equal to such grades as 302. Corrosion resisting properties will be affected by surface finish and aging heat treatment.

WELDABILITY

Excellent. Readily weldable by all commercial processes. Pre-heating and post-heating practices used for standard hardenable stainless grades are not required.

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Table AMS 2241. For further assistance please contact our Sales Dept / Laboratory.

Biggleswade

01767 604704

Birmingham

01889 576117

Bristol

0117 971 2800

Chelmsford

01245 466664

Ferndown

01202 893755

Gateshead

0191 469 5428

Horsham

01403 261981

Leeds

0113 307 5167

London

020 7241 2430

Nottingham

0115 925 4801

Norwich

01603 789878

www.smithmetal.com

sales@smithmetal.com