

# Carlson Alloy

## Nitronic 60<sup>®</sup> (UNS S21800)

Product Data Bulletin Nitronic 60

**Galling and wear resistant austenitic stainless steel that provides a significantly lower cost alternative to cobalt-bearing and high nickel alloys. Corrosion resistance superior to 304 in most media. Approximately twice the yield strength of 304 and 316. Possesses excellent high temperature oxidation resistance and low temperature impact resistance.**

### General Properties and Typical Applications

Nitronic 60 is an anti-galling and wear resistant austenitic stainless steel. It provides a significantly lower cost alternative to combat wear and galling when compared with cobalt-bearing and high nickel alloys. The uniform corrosion resistance of Nitronic 60 is superior to 304 in most media. Chloride pitting resistance is superior to 316. Room temperature yield strength is nearly twice that of 304 and 316. Nitronic 60 also possesses excellent high temperature oxidation resistance and low temperature impact resistance.

Due to its grain structure, the galling resistance of Nitronic 60 is superior to that of any other stainless steel. It resists wear, tearing or freeze up of both the primary and contact materials over a wide range of service temperatures. The elevated temperature wear resistance of Nitronic 60 is excellent despite its relatively low hardness when compared with cobalt and nickel-base wear alloys. It also performs well in metal-to-metal wear in nominally inert atmospheres. The cavitation erosion resistance of Nitronic 60 is superior to the austenitic stainless steels as well as high strength duplex (ferritic-austenitic) stainless steels.

The general corrosion resistance of Nitronic 60 falls between 304 and 316. However, in a wear system,

a galling or seizure failure occurs first followed by dimensional loss due to wear and finally corrosion. Although the general corrosion resistance of Nitronic 60 is not as good as 316, it does offer better chloride pitting, stress corrosion cracking and crevice corrosion resistance.

In high temperature service, Nitronic 60 exhibits carburization superior to 316L and 309. Its oxidation resistance is far superior to 304 and 316 and comparable to 309.

#### APPLICATIONS:

- Infrastructure bridge pin and hanger expansion joints, parking deck expansion joint wear plates.
- Hydroelectric Power - stems, wicket gate wear rings.
- Oil and Gas Production - pump wear rings, bushings, valve trim, seals, fittings, logging equipment and screens.
- Food Processing and Pharmaceuticals - galling resistant applications in sanitary equipment where lubricants can not be used.
- Chemical and Petrochemical - process valve stems, seats and trim, pump wear rings.

### Chemical Composition (Nominal Analysis, Percent)

Carbon, max. ....	0.10	Chromium.....	16.00 min. - 18.00 max.
Manganese.....	7.00 min. - 9.00 max.	Nickel.....	8.00 min. - 9.00 max.
Silicon .....	3.50 min. - 4.50 max.	Nitrogen.....	0.08 min. - 0.18 max.
Sulfur, max. ....	0.030		
Phosphorus, max. ....	0.060		

# Carlson Alloy

## Nitronic 60<sup>®</sup> (UNS S21800)

### Mechanical and Physical Properties

#### AVAILABLE PRODUCTS\*

##### Plate:

3/16" and thicker.  
Widths to 126",  
lengths to 480"

For larger dimensions -  
inquire

##### Plate Products:

plasma cut or machined rings  
and discs, cut bar, heads,  
rolled and tack-welded  
cylinders, and special cut  
shapes

Tensile Strength, ksi, min. ....	95
Yield Strength (0.2% offset), ksi, min. ....	50
Elongation in 2 in., (or 4D), %,min. ....	35
Hardness, Brinell, max. ....	241
Rockwell B, max. ....	100
Density, grams per cu. cm. ....	7.62
Electrical Resistivity, microhm-cm ....	98.2
Modulus of Elasticity, tension, psi x 10 <sup>-6</sup> ....	26.2
Coefficient of Thermal Expansion, in. / in./°F x 10 <sup>-6</sup>	
75° to 200°F.....	8.8
75° to 400°F.....	9.2
75° to 600°F.....	9.6
75° to 800°F .....	9.8
75° to 1000°F .....	10.0
75° to 1200°F .....	10.3
75° to 1400°F .....	10.5
75° to 1600°F .....	10.7
75° to 1800°F .....	11.0

### Galling Resistance

Unlubricated Galling Resistance of Stainless Steels  
Threshold Galling Stress in ksi (MPa)  
(Stress at which galling began)

Condition Nominal Hardness (Brinell)	Unlubricated Galling Resistance of Stainless Steels									NTRC 32	NTRC 60
	410	416	430	440C	303	304	316	17-4			
Hardened & Stress Relieved (352) - 410	3 (21)	4 (28)	3 (21)	3 (21)	4 (28)	2 (14)	2 (14)	3 (21)	46 (317)	50+(345)	
Hardened & Stress Relieved (342) - 416	4 (28)	13 (90)	3 (21)	21 (145)	9 (62)	24 (165)	42 (290)	2 (14)	45 (310)	50+(345)	
Annealed (159) - 430	3 (21)	3 (21)	2 (14)	2 (14)	2 (14)	2 (14)	2 (14)	3 (21)	8 (56)	36 (248)	
Hardened & Stress Relieved (560) - 440C	3 (21)	21 (145)	2 (14)	11 (76)	5 (34)	3 (21)	37 (255)	3 (21)	50+(345)	50+(345)	
Annealed (153) - 303	4 (28)	9 (62)	2 (14)	5 (34)	2 (14)	2 (14)	3 (21)	3 (21)	50+(345)	50+(345)	
Annealed (140) - 304	2 (14)	24 (165)	2 (14)	3 (21)	2 (14)	2 (14)	2 (14)	2 (14)	30 (207)	50+(345)	
Annealed (150) - 316	2 (14)	42 (290)	2 (14)	37 (255)	3 (21)	2 (14)	2 (14)	2 (14)	3 (21)	38 (262)	
H 950 (415) - 17-4 PH	3 (21)	2 (14)	3 (21)	3 (21)	2 (14)	2 (14)	2 (14)	2 (14)	50+(345)	50+(345)	
Annealed (235) Nitronic 32	46 (317)	45 (310)	8 (55)	50+(345)	50+(345)	30 (207)	3 (21)	50+(345)	30 (207)	50+(345)	
Annealed (205) Nitronic 60	50+(345)	50+(345)	36 (248)	50+(345)	50+(345)	50+(345)	38 (262)	50+(345)	50+(345)	50+(345)	

+ Did Not Gall (Note: Condition and Hardness apply to both horizontal and vertical axes.)

# Carlson Alloy

(UNS S21800) **Nitronic 60<sup>®</sup>**

<b>Wear Resistance</b>							
Wear Compatibility of Stainless Steel Couples Weight Loss, mg./1000 cycles							
Alloy	vs. 304	316	17-4PH	Ntrc 32	Ntrc 50	Ntrc 60	440C
Hardness Rockwell	B99	B91	C43	B95	B99	B95	C57
304	12.8						
316	10.5	12.5					
17-4	24.7	18.5	52.8				
Nitronic 32	8.4	9.4	17.2	7.4			
Nitronic 50	9.0	9.5	15.7	8.3	10.0		
Nitronic 60	6.0	4.3	5.4	3.2	3.5	2.8	
440C	4.1	3.9	11.7	3.1	4.3	2.4	3.8

<b>Corrosion Resistance</b>				
Media	Nitronic 60 Annealed	304 Annealed	316 Annealed	17-4 PH (H 925)
65% Boiling HNO <sub>3</sub>	0.060 in./yr.	0.012 in./yr.	0.012 in./yr.	0.132 in./yr.
1% HCl @ 35°C	0.010 in./yr.	0.053 in./yr.	--	0.024 in./yr.
2% H <sub>2</sub> SO <sub>4</sub> @ 80°C	0.045 in./yr.	0.243 in./yr.	0.011 in./yr.	0.021 in./yr.
5% H <sub>2</sub> SO <sub>4</sub> @ 80°C	0.521 in./yr.	1.300 in./yr.	0.060 in./yr.	--
10% FeCl <sub>3</sub> @ room temp (pitting test) 50 Hours	0.004 g./in. <sup>2</sup> No Pits	0.065 g./in. <sup>2</sup> Pitted	0.011 g./in. <sup>2</sup> Pitted	0.154 g./in. <sup>2</sup> Pitted
10% FeCl <sub>3</sub> @ R T with artificial crevices 50 hours	0.024 g./in. <sup>2</sup> Slight	0.278 g./in. <sup>2</sup> Heavy	0.186 g./in. <sup>2</sup> Heavy	-- --
5% Formic Acid @ 80°C	< .001 in./yr.	0.081 in./yr.	< .001 in./yr.	0.001 in./yr.
33% Boiling Acetic Acid	0.011 in./yr.	0.151 in./yr.	< .001 in./yr.	0.006 in./yr.
70% Hydrazine 168°F (76°C), 72 Hours	No reaction - Passed			
5% Salt Spray @ 95°F (35°C) 120 Hours	Nitronic 60 exhibited resistance to general rusting comparable to 304			

# Carlson Alloy

## Nitronic 60<sup>®</sup> (UNS S21800)

Product Data Bulletin Nitronic 60

### Carburization Resistance

Alloy		UTS		0.2% YS		Elongation % in 4xD	Reduction of Area %	Bend 1.5T
		ksi	(MPa)	ksi	(MPa)			
Nitronic 60	Unexposed	116.0	(800)	49.5	(341)	74.0	66.3	180°
	Exposed	91.5	(630)	58.0	(400)	19.0	21.6	100°
316L	Unexposed	76.0	(524)	30.0	(207)	68.0	74.4	180°
	Exposed	65.0	(448)	36.0	(248)	24.0	21.3	100°
309	Unexposed	99.0	(683)	41.0	(283)	54.0	64.7	180°
	Exposed	85.5	(589)	45.5	(313)	14.0	11.9	75°

Conditions: Duplicate tests exposed at 1800°F (982°C) for 2 hours in packed 90% graphite + 10% sodium carbonate.

### Oxidation Resistance

Test Temperature, F (C)	Static Oxidation Resistance				
	RA 333	310	Nitronic 60	304	
2100 (1149)	Before Descaling	3.1	4.6	16.5	1220
	After Descaling	12.2	15.7	23.2	1284
2200 (1204)	Before Descaling	10.1	10.1	26.1	2260
	After Descaling	16.7	20.6	35.4	2265

### Specifications

**ASME SA240**  
**ASTM A240**  
**ASTM A276**  
(Chemistry Only)

Information in this product data bulletin is not intended for specification purposes. All data should be considered as typical or average, except when listed as minimum or maximum values.

The applications cited will allow a potential user to consider this Carlson

alloy for a particular installation. But none of the information is to be construed as a warranty of fitness for any application.

As with all special-service materials, this alloy must be tested under actual service conditions to determine its suitability for a specific project.



**G.O. CARLSON Inc.**

*unsurpassed experience with specialty metals*

P.O. Box 526

Thorndale, PA 19372-0526

Telephone (610) 384-2800

Toll Free (800) 338-5622 (All USA & Canada)

Toll Free Customer Service (800) 972-3780 Fax (610) 383-3429